

### Description

DuoCrete SD mortar is used in the installation of the DuoGuard™ Hybrid Anode™ range into corrosion damaged reinforced concrete. The DuoCrete SD mortar is pre-mixed and packaged in a sealant tube and applied into pre-drilled holes in the concrete before the anode is inserted to generate an embedded unit.

The DuoCrete SD mortar facilitates activation of the DuoGuard anode unit in both applied current and galvanic current modes of operation. The cure time and physical properties have been designed to simplify installation and optimise performance.



### Features

- Specially formulated for application
- Pre-mixed for ease of use
- Single component
- Simple installation
- Long shelf life

### Advantages

- Enhances the performance of DuoGuard anodes
- Eliminates inconsistency associated with on-site mixing of mortars
- Minimal site labour requirement reduces costs
- Absence of site batching minimises waste
- Cost effective corrosion control solution

### Application

Application of the DuoCrete SD mortar shall be in accordance with the 'Installation Guidelines' and is summarised as follows:

DuoGuard anodes are typically installed at a spacing of 350-500 mm.

DuoGuard anodes are installed into pre-drilled holes of 30 mm diameter with the depth being dependent on the size of anode used. The DuoCrete SD mortar is gunned into the holes and must encapsulate the anode to ensure a large active surface area.

Following connection of the DuoGuard anodes, a current is applied for 1 week after which time the power supply is removed and the assembly can be covered with a repair mortar.

### Product Data

Packaging : 380 ml tubes, 20 units per box

Storage : Store dry in original containers

### Ancillary Materials

The following ancillary materials are also available from CPT Ltd;

- DuoGuard™ Hybrid Anode™
- Manganese dioxide reference electrode
- Monitoring equipment

### Limitations

DuoCrete SD mortar should not be applied at temperatures below 5°C.

For additional information relating to the installation of the DuoGuard system please refer to the **DuoGuard™ datasheet** and **Installation instructions**.

\*Dependant on local site conditions, including chloride concentration, concrete properties, humidity and temperature

# DuoCrete SD Mortar



### Health and Safety

Protective clothing must be worn. Wear gloves and eye protection at all times. For more information, refer to the DuoCrete SD material safety datasheet.

### Contact Details

For technical and sales support please contact us at;

**E-mail:**      [nigeld@cp-tech.co.uk](mailto:nigeld@cp-tech.co.uk)

**Address:**

Enterpriselab, The Sir Colin Campbell Building  
University of Nottingham Innovation Park  
Triumph Road  
Nottingham  
NG7 2TU

**Telephone** +44 (0)115 8229 430

**Fax**            +44 (0)115 9220 316

**[www.cp-tech.co.uk](http://www.cp-tech.co.uk)**