Data sheet



Formtex® / Formtex PSA®	Unit	Mean Value
Pore size	μm*	< 30
Air permeability	I/m²/sec	250
Water permeability	I/m²/sec	10
Water Retention Capacity	I/m²	1
Tear strength Machine direction	N	200
Tear strength Cross direction	N	185
Thickness at 2 kPa	mm	1.2
Thickness at 200 kPa	mm	0,8
Weight	g/m²	250
Composition	100% polypropylene	

^{* 1} μ m = 1/1000 mm

The values correspond to average results obtained in our laboratories and are indicative. The right is reserved to make changes at any time without notice.

Environment

The use of Formtex® eliminates the need for form oil and chemical release agents on the formwork. Furthermore, there is no need for coating or any other aftertreatment as the surface concrete has a very high quality.

Formtex® can be disposed of as ordinary household rubbish - when incinerated at temperatures higher that 600° C only CO, CO₂ and water are produced.

Quality Control

Fibertex Nonwovens A/S is certified under ISO9001 Quality Assurance system and regular Quality Assurance tests are carried out during the production of Formtex® in accordance with the ISO9001 Standards of Quality Assurance.



Fibertex Nonwovens A/S Tel Svendborgvej 16 Fa DK-9220 Aalborg Ø Em Denmark We

Tel. +45 96 35 35 35 Fax +45 98 15 85 55 Email: fibertex@fibertex.com Web: www.fibertex.com Web: www.formtex.dk



